



Lonestar Alpha Laboratories

Muscat : P.O. Box 1197, P.C 130, Muscat, Sultanate of Oman - Tel.: +968 24501524 / 5590, Fax : +968 24503814
 Muscat Chemistry Lab : P.O. Box 1197, P.C 130, Muscat, Sultanate of Oman - Tel.: +968 24504206, 24504924, Fax : +968 24502635
 Sohar : P.O. Box 84, P.C 327, Sohar Industrial Estate, Sultanate of Oman - Tel.: +968 26751755 / 920 / 976, Fax : +968 26751331
 Duqm : Tel.: +968 99278040, E-mail: duqm.lab@lonestartalpa.com
 Salalah : P.O. Box 1887, P.C 211, Tel.: +968 23213390, Fax: +968 23213391, E-mail: salalah.lab@lonestartalpa.com
 E-mail : info@lonestartalpa.com, Website: www.lonestartalpa.com

TEST CERTIFICATE

Report No.	LMCIV-870785/1	Date Reported	25 th April 2016
Customer Ref.	-	Date Received	19 th April 2016

Information Provided by the Customer

Customer For LAL	M/s. Stones World International Company LLC
Project	General
Project Customer	General
Consultant	General
Sample Description	Marble Stone (Moon Cream)

Sampled By	Customer	Sampling Date	Not Given
Sampled Brought By	Customer	Sampling Method	Not Given
Source of Sample	Not Given	Sampling Location	Not Given

Information Provided by Laboratory

Date Sample Tested	19 th April 2016	Test Location	LAL Muscat
--------------------	-----------------------------	---------------	------------

1. (i) Compressive Strength (ASTM C 170/C170M-2016)

Sample No.	Dry (MPa)
CIV-03260/1	154.9
CIV-03260/2	142.2
CIV-03260/3	131.4
CIV-03260/4	129.7
CIV-03260/5	149.7
Mean	141.6

(ii) Compressive Strength (ASTM C 170/C170M-2016)

Sample No.	Wet (MPa)
CIV-03260/6	129.0
CIV-03260/7	125.6
CIV-03260/8	126.2
CIV-03260/9	128.0
CIV-03260/10	119.3
Mean	125.6

2. Density (ASTM C 97/C97M-2015)

Sample No.	Bulk Specific Gravity	Unit Weight (kg/m ³)	Water Absorption %
CIV-03260/11	2.682	2692	0.4
CIV-03260/12	2.695	2700	0.2
CIV-03260/13	2.700	2705	0.2
CIV-03260/14	2.689	2697	0.3
CIV-03260/15	2.695	2700	0.2
Mean	2.692	2699	0.2





Lonestar Alpha Laboratories

Muscat : P.O. Box 1197, P.C 130, Muscat, Sultanate of Oman - Tel.: +968 24501524 / 5590, Fax : +968 24503814
Muscat Chemistry Lab : P.O. Box 1197, P.C 130, Muscat, Sultanate of Oman - Tel.: +968 24504206, 24504924, Fax : +968 24502635
Sohar : P.O. Box 84, P.C 327, Sohar Industrial Estate, Sultanate of Oman - Tel.: +968 26751755 / 920 / 976, Fax : +968 26751331
Duqm : Tel.: +968 99278040, E-mail: duqm.lab@lonestartalpa.com
Salalah : P.O. Box 1887, P.C 211, Tel.: +968 23213390, Fax: +968 23213391, E-mail: salalah.lab@lonestartalpa.com
E-mail : info@lonestartalpa.com, Website: www.lonestartalpa.com

Report No. LMCIV-870785/1

3. (i) Flexural Strength (ASTM C 880/C880M-2015)

Sample No.	Dry (MPa)
CIV-03260/16	7.0
CIV-03260/17	9.4
CIV-03260/18	6.0
CIV-03260/19	7.9
CIV-03260/20	8.3
Mean	7.7

(ii) Flexural Strength (ASTM C 880/C880M-2015)

Sample No.	Wet (MPa)
CIV-03260/21	6.1
CIV-03260/22	5.9
CIV-03260/23	6.5
CIV-03260/24	7.1
CIV-03260/25	7.3
Mean	6.6

4. (i) Modulus of Rupture (ASTM C 99/C99M-2015)

Sample No.	Dry (MPa)
CIV-03260/26	7.0
CIV-03260/27	8.0
CIV-03260/28	6.7
CIV-03260/29	5.6
CIV-03260/30	6.5
Mean	6.8

(ii) Modulus of Rupture (ASTM C 99/C99M-2009)

Sample No.	Wet (MPa)
CIV-03260/31	5.4
CIV-03260/32	5.6
CIV-03260/33	5.7
CIV-03260/34	6.0
CIV-03260/35	5.1
Mean	5.6



For and on behalf of Lonestar Alpha Laboratories
Muscat